



Bakelite resistivity

Some New Data

(from Puricelli)

G. Belli, P. Vitulo

environment T		nd		24.00		26.00		21.50		23.00		27.00	
humidity H%		nd		36.00		43.00		44.00		39.00		43.00	
id. panels	prod. Date	Resistivity	tpanel	Resistivity PAVIA	tpanel	Resistivity	tpanel	Resistivity	tpanel	Resistivity	tpanel	Resistivity	tpanel
DATA MISURA	Data di produz.	14/03/2011		22/04/2011		03/05/2011		04/05/2011		06/05/2011		12/05/2011	
Giacosa A v. 8,3	05/05/2011									13.90	22.00	15.39	26.50
Giacosa B v. 8,3	05/05/2011									12.07	22.00	16.07	26.50
Giacosa C v. 8,3	05/05/2011									9.41	22.00	12.56	26.50
Enso D 229 g.	05/05/2011									1.52	22.00	2.26	26.50
Enso E 240 g.	05/05/2011									1.00	22.00	1.55	26.50
Giacosa A v. 8,5	29/04/2011					19.53	28.60	11.71	21.60	10.15	22.00	13.17	26.50
Giacosa B v. 8,5	29/04/2011					21.26	28.60	11.49	21.60	12.07	22.00	13.33	26.50
Giacosa C v. 8,5	29/04/2011					23.31	28.60	12.18	21.60	11.03	22.00	13.17	26.50
Enso D 229 g.	29/04/2011					6.30	28.60	3.62	21.60	3.35	22.00	3.99	26.50
Enso E 240 g.	29/04/2011					3.61	28.60	1.63	21.60	1.47	22.00	1.86	26.50
Giacosa vol. 8,05 - XxE0226	18/04/2011			9.46	23.30					7.10	22.00	8.81	26.50
Giacosa vol. 8,05 - XxD0225	18/04/2011			8.97	23.30					8.10	22.00	9.76	26.50
Giacosa vol. 8,05 - XxC0224	18/04/2011			7.59	23.30					7.20	22.00	8.6	26.50
Giacosa vol. 7,3 - XxD0223	18/04/2011			11.25	23.30					9.00	22.00	10.51	26.50
Giacosa vol. 7,3 - XxA0222	18/04/2011			16.29	23.30					13.91	22.00	14.01	26.50
Giacosa A Vol 8,5 (Kraft_febbr)	14/03/2011									2.00	22.00	2.32	26.50
Giacosa B Vol 8,5 (Kraft_febbr)	14/03/2011									3.31	22.00	3.53	26.50
Giacosa C Vol 8,5 (Kraft_febbr)	14/03/2011									1.08	22.00	1.17	26.50
Giacosa D Vol 8,5 (Kraft_febbr)	14/03/2011									1.92	22.00	2.1	26.50
Giacosa E Vol 8,5 (Kraft_febbr)	14/03/2011									4.84	22.00	5.18	26.50
Giacosa A VOL 8,5 (Kraft_febbr)	11/03/2011	5.00	20.00							5.66	22.00	5.81	26.50
Giacosa B VOL 8,5 (Kraft_febbr)	11/03/2011	4.50	20.00							7.19	22.00	7.19	26.50
Giacosa C VOL 8,5 (Kraft_febbr)	11/03/2011	4.50	20.00							6.21	22.00	6.62	26.50
Giacosa D VOL 8,5 (Kraft_febbr)	11/03/2011	6.60	20.00							6.95	22.00	8.4	26.50
Giacosa E VOL 8,5 (Kraft_febbr)	11/03/2011	8.30	20.00							10.84	22.00	10.3	26.50

Comments

- ✓ The previous table shows many measurements made in (and by) Puricelli on SMALL (25 cm x 25) cm samples.
- ✓ Of them only 5 samples have been measured by Pavia (we were not aware of the majority of them -10 samples-)
- ✓ Due to the previous comment we cannot draw now any conclusion